

Interpretation of Nuclear Quadrupole Resonance Spectra in Doped La_2CuO_4

S. Pliberšek and P. F. Meier

Physics Institute, University of Zurich, CH-8057 Zurich, Switzerland

Abstract

The nuclear quadrupole resonance (NQR) spectrum of strontium doped La_2CuO_4 surprisingly resembles the NQR spectrum of La_2CuO_4 doped with excess oxygen, both spectra being dominated by a main peak and one principal satellite peak at similar frequencies. Using first-principles cluster calculations this is investigated here by calculating the electric field gradient (EFG) at the central copper site of the cluster after replacing a lanthanum atom in the cluster with a strontium atom or adding an interstitial oxygen to the cluster. In each case the EFG was increased by approximately 10 % leading unexpectedly to the explanation that the NQR spectra are only accidentally similar and the origins are quite different. Additionally the widths of the peaks in the NQR spectra are explained by the different EFG of copper centres remote from the impurity. A model, based on holes moving rapidly across the planar oxygen atoms, is proposed to explain the observed increase in frequency of both the main and satellite peaks in the NQR spectrum as the doping concentration is increased.

A large amount of information about static and dynamic properties of high-temperature superconducting oxides has been provided by nuclear magnetic resonance (NMR) and nuclear quadrupole resonance (NQR) experiments¹. In certain materials, however, some NMR and NQR results are still not completely understood. In part, this is related to the lack of theoretical support since, to date, only a few first-principles calculations have addressed the local charge and spin density distributions. An example of these unresolved problems is the interpretation of the NQR spectra in doped La_2CuO_4 . This material becomes superconducting only upon alloying on the La site or changing the oxygen content. There is therefore considerable interest in understanding the changes in the local electronic structure that the various dopants induce.

Experimental observations² of NQR spectra for stoichiometric La_2CuO_4 show one sharp peak at 33 MHz assigned to ^{63}Cu . Upon doping with strontium, a second weaker line appears at a somewhat higher frequency³⁻⁷. This was called B-line to distinguish it from the main resonance line (A). Increasing the concentration of dopants causes both peaks to broaden as well as increase in frequency slightly. Similar behaviour is observed^{8,9} when oxygen is used as the dopant. This produces an additional line which is so close in frequency to the B-line frequency of the Sr-doped spectra that both lines were attributed to the same physical origin. Hence it was proposed that holes are localized in CuO_6 octahedra adjacent to the charged dopants. These holes, if pinned at least for times of the order of microseconds, would then cause the NQR B-lines. This interpretation was corroborated by results from ab-initio calculations¹⁰ on the magnitude of the copper NQR frequency which showed that the Sr- and O-dopants themselves had very different effects on the NQR frequency but the frequency shift for a copper adjoining a site occupied by a localized hole matched the experimental results very closely. Although there is strong evidence for various kinds of charge inhomogeneities in doped lanthanum cuprate, the occurrence of static pinned holes proved elusive. In addition, there are some subtle differences between the NQR spectra of Sr- and O-doped samples, such as the asymmetry of the electric field gradient of the B-lines, which are not explained by the above model.

In this work, we report on results of density functional cluster calculations that address the changes in the electric field gradients (EFGs) in La_2CuO_4 upon doping. Four different cluster models were used to simulate various experimental situations:

(M_α) $\text{CuO}_6/\text{Cu}_4\text{La}_{10}$ represents the La_2CuO_4 crystal and used to obtain the EFG at the central copper site

(M_β) $\text{CuO}_6/\text{Cu}_4\text{La}_9\text{Sr}$ represents the $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ crystal in the dilute limit $x \rightarrow 0$

(M_γ) $\text{CuO}_6/\text{Cu}_4\text{La}_{10}$ and $\text{CuO}_6/\text{Cu}_4\text{La}_9\text{Sr}$, as above, but where positive charges are placed on each planar oxygen. This model is proposed to investigate the influence of holes that are moving rapidly across the planar oxygen sites

(M_δ) $\text{CuO}_7/\text{Cu}_4\text{La}_{10}$, the same as $\text{CuO}_6/\text{Cu}_4\text{La}_{10}$ but where an extra oxygen atom occupies an interstitial site, representing the $\text{La}_2\text{CuO}_{4+\delta}$ crystal in the dilute limit $\delta \rightarrow 0$.

Recently, extensive cluster studies for the pure La_2CuO_4 system have been presented¹¹. Spin-polarized calculations at the Hartree-Fock (HF) level and with the density functional (DF) method with gradient corrections to the exchange and correlation functionals have been performed for clusters comprising up to 9 Cu atoms in a CuO_2 -plane. It has been shown that an acceptable estimate of the EFG at the copper site can already be obtained with DF calculations with a small cluster ($\text{CuO}_6/\text{Cu}_4\text{La}_{10}$) where a $(\text{CuO}_6)^{10-}$ -ion is treated with an all-electron basis set and 4 surrounding Cu and 10 La atoms are represented by bare pseudopotentials. This is the cluster which is chosen as model M_α in the present work. It is embedded in a lattice of 2464 point charges. The positions of some point charges were changed in such a way that the correct Madelung potential in the central region of the cluster was reproduced. All atomic positions were located according to the tetragonal phase with lattice constants¹² $a = 3.77 \text{ \AA}$ and $c = 13.18 \text{ \AA}$ and with a Cu-O(apex) distance of $2.40 \text{ \AA}$. For the cluster atoms standard triple-zeta (6-311 G) basis sets were employed. All calculations were spin-polarized and were performed with the Gaussian94 and Gaussian98 programs¹³. In the DF calculations the correlational functional of Lee, Yang, and Parr¹⁴ was combined with the Becke¹⁵ exchange functional, which also includes corrections based on the gradient of the electron density.

For model M_α the density functional calculations with the BLYP functional give for V_{zz} , the z-component of the EFG, at the Cu site a value of 1.419 a.u.. This corresponds to a ^{63}Cu quadrupole frequency of 35 MHz if a quadrupole moment $Q(^{63}\text{Cu}) = -.211 \text{ b}$ is adopted¹⁶. The experimental ^{63}Cu NMR spectrum of pure La_2CuO_4 shows² a narrow peak at 33 MHz. The good agreement between theory and experiment may be accidental in view of the small cluster size. Furthermore, there is no general consensus about the precise value of $Q(^{63}\text{Cu})$. Other sources of inaccuracy are due to the limited basis set used for the representation of the atomic orbitals and the choice of the exchange and correlation functionals for the treatment of the generalized gradient approximations beyond the local density approximations. Since we focus in this paper on the relative changes of the local electronic structure around the copper atom which are induced by models for various doping effects, all calculations are carried out at the same level of approximation. We expect then that the difference between EFG values calculated for different clusters will not significantly be influenced by the above inaccuracies.

It should further be remarked that the EFG cannot be explained in a simple one-electron (or rather one-hole) picture. The theoretical value results from cancellations between relatively large individual contributions from the various atomic shells which are listed in the second column of Table I.

It has been shown¹¹ that other choices of the exchange-correlation functional have little influence on V_{zz} . HF calculations, however, produce a V_{zz} -value that is 36 % higher. This discrepancy between DF and HF results for the EFG at Cu sites has also been found in previous calculations for the $\text{YBa}_2\text{Cu}_3\text{O}_7$ system. It is further discussed in Ref.^{17,18} but is not the topic of the present work which focusses on the relative changes in V_{zz} upon doping.

To simulate the influence of doping with Sr, the calculations were then repeated for the $(\text{CuO}_6)^{10-}$ -ion with the La^{3+} on top of the Cu replaced by Sr^{2+} (model M_β). This simulates a situation where the hole introduced has moved to a place far from the cluster region or is distributed over several sites. The resulting changes in the contributions to V_{zz} with respect to the undoped system are given in the third column of Table I. The EFG is increased by

10.3 % which is very close to the observed difference of about 3 MHz in $^{63}\nu_Q$ between the additional peak (B-line) and the main peak (A-line). It should be noted that in models M_α and M_β the same atomic positions were used. Structural changes induced by replacing the lanthanum atom by strontium are thus not accounted for.

At the Cu sites adjacent to the central Cu ion of the cluster, the replacement of La^{3+} by Sr^{2+} leads to an increase of V_{zz} by 1 %. This explains the observed broadening of the main peak (A-line) in $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$.

Similar cluster models (M_α for pure and M_β for Sr-doped La_2CuO_4) have previously been investigated by Martin¹⁰ with HF calculations with results which drastically differ from those of our DF calculations. We therefore also performed HF calculations for the clusters M_α and M_β . For the undoped system, our HF result ($V_{zz} = 1.94$ a.u.) is in broad agreement¹⁹ with his ($V_{zz} = 1.84$ a.u.) and also with the value reported by Sulaiman et al.²⁰ ($V_{zz} = 2.23$ a.u.). For the Sr-doped system, however, the results differ strongly. In Ref.¹⁰, an increase of V_{zz} by 1.5 % was reported while our HF calculations predict a change by 5.9 %.

Our DF results thus suggest that the B-line observed in La_2CuO_4 upon doping with strontium simply originates from the Cu atoms next to the positions of the dopant atoms. If the models M_α and M_β adequately describe the local electronic structure around the strontium dopant, a separate oxygen NQR spectrum is to be expected due to ^{17}O nuclei that bridge the strontium atom and its nearest copper atom. For model M_α , our calculations give $V_{zz} = 0.28$ a.u. for the apical oxygens. For model M_β they predict $V_{zz} = 0.15$ a.u. for the bridging O(a). The number of oxygen nuclei that exhibit this spectrum, however, only amounts to $p_{\text{O}}x/4$ per formula unit where p_{O} is the abundance of ^{17}O nuclei in the sample. It should be noted, however, that the clusters used in this work were not designed for studying the EFGs at the oxygen sites. Indeed, using larger clusters for the undoped system, the values of the EFGs at the apical oxygens turn out to be smaller and closer to the experimental values of 0.22 a.u.. The pronounced calculated reduction of V_{zz} upon replacing a La by a Sr atom, however, is related to the charge redistribution and will persist also in more elaborate calculations.

Next we investigate the changes induced by an interstitial oxygen atom O(i) at the location (a/2,0,c/4). In the tetragonal structure, this site is surrounded by four nearest oxygen neighbours at a distance of 2.09 Å for the geometry parameters used here, followed by four La and four Cu. The latter form two pairs which lie in adjacent CuO₂-planes and have the four O(a) atoms at corresponding apical positions. This interstitial location for O(i) is undisputed^{21,22}. It is also evident that the squeezing in of the excess oxygen into the interstice will cause a relaxation of the atoms in the immediate neighborhood. The La positions seem to be unchanged²². The EFG value at the copper site depends crucially on the precise position of the apical oxygen near the interstitial site, even though the extent of its displacement is disputed^{22–24}. Therefore we determined this position of the O(a) which also minimised the energy of our cluster model M_δ . For this, the cluster CuO₆/Cu₄La₁₀ was extended by including an additional oxygen O(i). This model also accounts for that situation where no additional holes are present in the cluster region.

The positions of all cluster atoms and point charges of the background were first frozen except those of the apical oxygen with coordinates (x_a, y_a, z_a) nearest to the O(i) which was allowed to move on the plane $y_a = 0$. An energy minimum was found for $x_a = -0.64$ Å and $z_a = 2.26$ Å. At this position, the distance to the interstitial oxygen is 2.73 Å. This corresponds to a tilt of the O(a) by 16° which is reasonable when compared to experimental information^{22–24}. Next the positions of the three other apical oxygens coordinated with O(i) (which are represented by point charges only) were displaced accordingly. With this geometry, the EFG is no longer axially symmetric and the eigenvector of the largest component is rotated by 4° from the z-axis. The asymmetry of the EFG tensor amounts to $\eta = 0.05$ in approximate agreement with the experimental⁹ value of 0.07. The largest eigenvalue of the EFG is 1.575 a.u. which is 11.0 % larger than in model M_α . This corresponds to a shift in frequency of 3.8 MHz. HF calculations by Martin¹⁰ which were carried out without taking the local distortions around the interstitial oxygens into account, showed an increase of about 5 MHz with respect to the results for the undoped case.

Our model M_δ can thus account for the occurrence and position of the satellite peak

in the NQR spectrum of $\text{La}_2\text{CuO}_{4+\delta}$. The close agreement of the frequencies of the B-lines in strontium- and oxygen-doped lanthanum cuprate is therefore only accidental. The physical origins of the B-lines are quite different in the two cases. This is also reflected in the asymmetry parameter η which is zero in model M_β by symmetry. Repeating the calculations for a cluster with atomic positions chosen according to the orthorhombic structure yields an asymmetry of $\eta = 0.01$ for model M_β .

Since each interstitial oxygen has four nearest copper atoms, the intensity of the B-line in $\text{La}_2\text{CuO}_{4+\delta}$ is thus expected to increase with 4δ which is also in agreement with the experiments⁹.

Finally we study the shift of the A-line upon doping. We adopted model M_γ where holes rapidly move across the planar oxygen sites. For a rough estimation, positive point charges $x/2$ were placed near the planar oxygen sites in the cluster $\text{CuO}_6/\text{Cu}_4\text{La}_{10}$. To be precise, point charges with values $x/8$ were put at positions where the $2p_x$ and $2p_y$ orbitals of the planar oxygens attain their extremal values. The calculations were performed for $x = 0.01$, 0.02 , and 0.04 , respectively. In the fourth column of Table I, the corresponding changes in the contributions to V_{zz} with respect to the undoped system, which turned out to be linear in x , are listed for $x = 0.04$. We obtain a shift $d(\log V_{zz})/dx \approx 0.7$ which is in reasonable agreement with the experimental value $d(\log \nu_Q)/dx \approx 0.6$ since no account is given to the fact that the lattice constants also slightly change with the doping concentration. Applying the same procedure to model M_β yields $d(\log V_{zz})/dx \approx 0.6$.

Our conclusions are as follows. The results obtained with the cluster $\text{CuO}_6/\text{Cu}_4\text{La}_9\text{Sr}$ (model M_β) predict an increase of the EFG at the Cu-site immediately adjacent to the Sr by 10 %. This would explain the occurrence and position of the NQR B-line in $\text{La}_{2-x}\text{Sr}_x\text{CuO}_4$ for $x \rightarrow 0$. In addition, the observed broadening of the A-line with increasing doping concentration could be attributed to the small shifts calculated for Cu sites not immediately adjacent to the Sr. Next, the shift of the A-line with increasing x could be explained by holes moving rapidly across the planar oxygens (model M_γ). We have shown that by introducing excess oxygen in $\text{La}_2\text{CuO}_{4+\delta}$ (model M_δ), the EFG at the Cu is also increased by an amount

which accidentally is about the same as doping with Sr produces. Hence our results disagree with previous interpretations of the Cu NQR spectra in the doped La_2CuO_4 system, in particular that of Martin¹⁰ which attribute the origin of the B-lines to localized holes that are introduced either by Sr or O doping.

We express our gratitude to T. A. Claxton for enlightening discussions and critical reading of the manuscript. We gratefully acknowledge the help of P. Hüsler and E. P. Stoll. This work is partially supported by the Swiss National Science Foundation.

REFERENCES

- ¹ For a review, see e. g. C. H. Pennington and C. P. Slichter, *Physical Properties of High Temperature Superconductors II*, Ed. D. M. Ginsberg, World Scientific (1990).
- ² T. Imai, C.P. Slichter, K. Yoshimura, and K. Kosage, *Phys. Rev. Lett.* **70**, 1002 (1993).
- ³ K. Yoshimura, T. Imai, T. Shimuzu, Y. Ueda, K. Kosuge, and H. Yosuka, *J. Phys. Soc. Japan* **58**, 3057 (1989).
- ⁴ K. Kumagai and Y. Nakamura, *Physica C* **157**, 307 (1989).
- ⁵ Y. Nakamura and K. Kumagai, *Physica C* **165/166**, 1303 (1990).
- ⁶ K. Yoshimura, T. Uemura, M. Kato, K. Kosuge, T. Imai, and H. Yasuoka, *Hyperfine Interactions* **79**, 867 (1993).
- ⁷ Y.-Q. Song, M. A. Kennard, M. Lee, K. R. Poeppelmeier, and W. P. Halperin, *Phys. Rev. B* **57**, 712 (1998).
- ⁸ P. C. Hammel, A. P. Reyes, S-W. Cheong, Z. Fisk, and J. E. Schirber, *Phys. Rev. Lett.* **71**, 440 (1993).
- ⁹ B. W. Statt, P. C. Hammel, Z. Fisk, S-W. Cheong, F. C. Chou, D. C. Johnston, and J. E. Schirber, *Phys. Rev. B* **52**, 15575 (1995).
- ¹⁰ R. L. Martin, *Phys. Rev. Lett.* **75**, 744 (1995).
- ¹¹ P. Hüsler, H. U. Suter, E. P. Stoll, and P. F. Meier, *cond-mat/9905246*
- ¹² *Copper Oxide Superconductors*, Ch. P. Poole, T. Datta and H.A. Farach, Wiley-Interscience Publication.
- ¹³ M. J. Frisch et al., *Gaussian 98*, Revision A.5, (Gaussian, Inc., Pittsburgh PA, 1998).
- ¹⁴ C. Lee, W. Yang, and R. G. Parr, *Phys. Rev. B* **37**, 785 (1988).
- ¹⁵ A. D. Becke, *Phys. Rev. A* **38**, 3098 (1988).

- ¹⁶ R. M. Sternheimer, Phys. Rev. B **41**, 220 (1990).
- ¹⁷ P. Hüsser, E. P. Stoll, H. U. Suter, and P. F. Meier, Physica C **294**, 217 (1998).
- ¹⁸ H. U. Suter, P. Hüsser, E. P. Stoll, S. Schafroth, and P. F. Meier, Hyperfine Interactions, in press.
- ¹⁹ The value $^{63}\nu_Q = 38.9$ MHz given in Ref.¹⁰ was converted into an electric field gradient using $Q(^{63}\text{Cu}) = -.18$ b for the quadrupole moment.
- ²⁰ S. B. Sulaiman, N. Sahoo, T. P. Das, and O. Donzelli, Phys. Rev. B **42**, 7082 (1991).
- ²¹ Most of the experimental information is of course available for the orthorhombic structure. For comparison, we will use the tetragonal structure.
- ²² C. Chaillout, Phys. Rev. B **44**, 5141 (1991). C. Chaillout, S. W. Cheong, Z. Fisk, M. S. Lehmann, M. Marezio, B. Morosin and J. E. Schirber, Physica C **158**, 183 (1989).
- ²³ P. G. Radaelli, J. D. Jorgensen, A. J. Schultz, B. A. Hunter, J. L. Wagner, F. C. Chou, and D. C. Johnston, Phys. Rev. B **48**, 499 (1993).
- ²⁴ F. Cordero, C. R. Grandini, R. Cantelli, Physica C **305**, 251 (1998).

TABLES

TABLE I. Contributions to the EFG component V_{zz} in atomic units from the nuclei within the cluster, from the point charges around the cluster, and from the individual shells. The “remainder” lists just the (small) rest of all other contributions that cannot be assigned to a particular shell. The second column shows the values for pure La_2CuO_4 (model M_α). In the third and forth column the changes are given which result when one La^{3+} is replaced by Sr^{2+} (model M_β) and for mobile holes corresponding to $x = 0.04$ (model M_γ), respectively.

	pure	Sr doped	holes x=0.04
Nuclei	0.375	0.003	0.000
Point charges	0.012	0.000	-0.002
p_x, p_y	-2.393	0.012	0.013
p_z	0.770	0.028	0.003
$d_{x^2-y^2}, d_{xy}$	-15.163	0.043	0.011
$d_{3z^2-r^2}$	8.829	0.040	0.011
d_{yz}, d_{zx}	9.003	0.002	0.001
Remainder	-0.012	0.019	0.007
Total	1.419	0.147	0.044